



CP Oil

CP Oil is a low-viscosity, corrosion-preventive oil developed for the lubrication of air tools and other pneumatic equipment lubricated through air line lubricators, especially where the compressed air has high moisture content.

CP Oil is formulated to provide excellent rust and corrosion protection and good wear protection for pneumatic tools, resulting in extended tool life. It has excellent metal-wetting ability to displace moisture from metal surfaces, and may be used as a rust preventive oil for metal parts stored indoors.

Applications

- Air tools and other pneumatic equipment lubricated through air line lubricators
- Rust and corrosion-preventive oil for metal parts stored indoors
- Lightly loaded plain and rolling-element bearings exposed to moisture

Features/Benefits

- Excellent rust and corrosion protection
- Excellent metal-wetting ability
- Good oiliness properties for wear protection
- Does not form lacquer or gum on metal surfaces
- Emulsifiable for easy removal from metal parts

**Corrosion-
Preventive
Air Tool Lubricant**

CONTACT INFORMATION

**Phillips66
Lubricants.com**

U.S. Customer
Service:
1-800-368-7128

Technical Hotline:
1-877-445-9198

International
Customer Service:
1-832-765-2500

E-mail address:
**lubricants@
p66.com**



CP Oil

Typical Properties

| ISO Grade | 22 | 32 |
|----------------------------------|-----------|-----------|
| Specific Gravity @ 60°F | 0.856 | 0.865 |
| Density, lbs/gal @ 60°F | 7.13 | 7.20 |
| Color, ASTM D1500 | 0.5 | 0.5 |
| Flash Point COC, °C (°F) | 230 (446) | 233 (451) |
| Pour Point, °C (°F) | -29 (-20) | -27 (-17) |
| Viscosity, | | |
| cSt @ 40°C | 22.0 | 32.1 |
| cSt @ 100°C | 4.4 | 5.4 |
| SUS @ 100°F | 115 | 166 |
| SUS @ 210°F | 41.1 | 44.4 |
| Viscosity Index | 109 | 102 |
| Acid Number, ASTM D974, mg KOH/g | 0.05 | 0.05 |
| Ash Content, ASTM D482, wt % | Nil | Nil |
| Foam Test, ASTM D892, Seq. I, ml | 0/0 | 0/0 |
| Rust Test, ASTM D665 A | Pass | Pass |

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3apps.phillips66.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

© 2015 Phillips 66 Company. Phillips 66, 76, Conoco, Liquid Titanium and their respective logos and products are trademarks of Phillips 66 Company in the U.S.A. and other countries.