



GLW

GLW is a premium quality, extreme-pressure (EP) industrial gear oil developed for the lubrication of heavily loaded enclosed gear drives operating under severe service conditions. It is specially formulated to quickly separate from water to maintain effective lubrication in the presence of water. It is particularly recommended for use in industrial and mining equipment operating in contaminated environments where an AGMA EP gear oil with excellent water-separating properties is specified or preferred.

GLW is formulated to provide excellent lubricity and wear protection even in the presence of water and other contaminants. It has high load-carrying capacity, high film strength, and protects against rust and corrosion for extended equipment life. It has good oxidation resistance and thermal stability at high temperatures and is formulated with "clean gear" additive technology to minimize deposit formation and provide outstanding gearbox cleanliness. It has good seal compatibility, excellent water-separating properties and is resistant to excessive foam buildup that can interfere with proper lubrication.

GLW is recommended for use in Joy Machinery longwall mining equipment as well as other mining, industrial and heavy mobile equipment operating under extreme loads and/or exposed to water contamination.

Applications

- Enclosed gear drives of longwall mining machinery
- Enclosed industrial gear drives operating in the presence of water, such as in steel mills and rock quarries
- Gear drives and pinion stands of metal rolling mills, ball mills and cement mills
- Enclosed gear drives on excavation and heavy construction equipment

GLW meets the requirements of the following industry and OEM specifications:

- ANSI/AGMA Standard 9005-E02, Anti-Scuff/Anti-Wear (EP) Oils
- DIN 51517 Part 3, Lubricating Oils, Type CLP
- Fives Cincinnati P-74 (ISO VG 220), P-59 (ISO VG 320) (approved)
- German Steel Industry SEB 181226, Type CLP
- ISO 12925-1, Type L-CKC & Type L-CKD

**Severe-Duty,
Extreme-Pressure
Industrial
Gear Oil;
Separates From
Water**

CONTACT INFORMATION

**Phillips66
Lubricants.com**

U.S. Customer
Service:
1-800-368-7128

Technical Hotline:
1-877-445-9198

International
Customer Service:
1-832-765-2500

E-mail address:
**lubricants@
p66.com**



- Joy Mining Machinery TO-MEP (ISO VG 220), TO-HEP (ISO VG 320), TO-HD (ISO VG 460)
- U.S. Steel 224

Features/Benefits

- Excellent performance in wet or contaminated gearboxes
- Outstanding load-carrying capacity
- Excellent protection against scuffing and wear
- Good oxidation resistance and thermal stability
- Outstanding deposit control for gearbox cleanliness
- Protects against rust and corrosion
- Excellent water-separating properties
- Good seal compatibility
- Environmentally responsible; does not contain chlorinated paraffins

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

© 2015 Phillips 66 Company. Phillips 66, 76, Conoco, Liquid Titanium and their respective logos and products are trademarks of Phillips 66 Company in the U.S.A. and other countries.



GLW

Typical Properties

ISO Grade	220	320	460
AGMA Grade	5 EP	6 EP	7 EP
Specific Gravity @ 60°F	0.890	0.894	0.898
Density, lbs/gal @ 60°F	7.41	7.44	7.48
Color, ASTM D1500	4.5	5.0	5.5
Flash Point (COC), °C (°F)	249 (480)	254 (489)	254 (489)
Pour Point, °C (°F)	-27 (-17)	-18 (0)	-15 (5)
Viscosity,			
cSt @ 40°C	220	320	460
cSt @ 100°C	18.7	23.7	32.0
SUS @ 100°F	1,164	1,706	2,457
SUS @ 210°F	95.5	118	157
Viscosity Index	95	94	101
Acid Number, ASTM D974, mg KOH/g	1.09	1.09	1.09
Copper Corrosion, ASTM D130	1b	1b	1b
Demulsibility, ASTM D1401, 30 minutes @ 180°F	Pass	Pass	Pass
Falex Pin & Vee Block True Load, ASTM D3233-B, lbs	>4,250	>4,250	>4,250
Foam Test, ASTM D892, Seq. I, ml	0/0	0/0	0/0
Four-Ball EP, ASTM D2783,			
LWI, kgf	57	57	57
Weld Load, kgf	270	270	270
FZG Scuffing Test, ASTM D5182, Failure Load Stage	>12	>12	>12
Oxidation Stability, ASTM D2893,			
Viscosity Increase @ 121°C, %	4.6	4.9	5.0
Rust Test, ASTM D665 B	Pass	Pass	Pass
Timken OK Load, ASTM D2782, lb	70	70	70

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3apps.phillips66.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

© 2015 Phillips 66 Company. Phillips 66, 76, Conoco, Liquid Titanium and their respective logos and products are trademarks of Phillips 66 Company in the U.S.A. and other countries.