Q8 Heinichen 46

Applications

Q8 Heinichen 46 is designed for a wide range of hydraulic equipment.

Specifications

- MAN 698
- ISO 6743/4, category HM
- DIN 51524 part 2, category HLPD

Benefits

- Optimum anti-wear performance, based on a zincdiakyldithiophosphate additive
- Long service life due to high thermal and oxidation stability for high temperature applications
- Trouble-free operation due to the unique combination of outstanding foam, air release and filterability characteristics
- Emulsifies entrained water

References

Q8 Heinichen meets the requirements of most hydraulic component manufacturers

Formulation

- Paraffinic mineral oils
- Anti-wear additive
- Rust inhibitor
- Anti-oxidant
- Rust inhibitor
- Anti-foam agent
- Corrosion inhibitor
- Detergent additive

Typical Inspection Data

| | Method | Units | Inspection Data |
|--------------------------------|--------|--------------------|-----------------|
| ISO Viscosity Grade | - | - | 46 |
| Absolute Density, 15 °C | D 4052 | kg/m ³ | 874 |
| Kinematic Viscosity, 40 °C | D 445 | mm ² /s | 46.0 |
| Kinematic Viscosity, 100 °C | D 445 | mm²/s | 6.72 |
| Viscosity Index | D 2270 | - | 98 |
| Flash Point | D 92 | °C | 222 |
| Pour Point | D 97 | °C | -24 |
| Colour | D 1500 | - | L1.0 |
| Copper Strip, 3 h, 100 °C | D 130 | - | 1 |
| Rust Test, Proc. A and B, 24 h | D 665 | - | pass |
| Total Acid Number | D 974 | mg KOH/g | 0.4 |
| Foam | | | |
| 5 min blowing, seq. 1/2/3 | D 892 | ml | 5/10/5 |
| 10 min settling, seq. 1/2/3 | | ml | 0/0/0 |

Health and Safety

Reference should be made to the relevant Q8 Material Safety Data Sheet before use.

Mar 12



Kuwait Petroleum International Lubricants (UK) Ltd

Knowsthorpe Gate, Leeds LS9 0NP. UK

For further assistance contact the Technical help line Telephone +44 (0) 113 2365 223, Fax +44 (0) 870 238 4673 For Customer Sales Contact, Tel +44 (0) 113 2365 204, Fax +44 (0) 113 2485 026. www.Q80ils.co.uk

