

DESCRIPTION

Synthetic Polyolester oils for refrigerating compressors using HFC refrigerants.

APPLICATIONS

- Compatible with all kinds of HFC type refrigerants : R134a, R404A, R407C, R410A, R507, R23...
- The **PLANETELF ACD 32, 46** et **68** are suitable for piston compressors.
- The **PLANETELF ACD 68, 100FY, 150FY** et **220FY** are suitable for rotary compressors (screw or centrifugal)

PROPERTIES

- ASHRAE thermal stability test confirms the excellent behaviour of the lubricant at high temperature in presence of refrigerant, water, and metallic components.
- Neutral behaviour with the refrigerating equipments:
 - Anti-rust, anti-corrosion properties with copper metals.
 - Compatibility with varnishes, elastomers and paints.
 - High resistance to hydrolysis
- Low dilution of refrigerant in oil for the high viscosity grades, for good lubricity and oil separation properties (low carry-over)
- The good miscibility of the fluid viscosities of **PLANETELF ACD** allows a good oil return property, specially in dry-ex equipments. Oil will not reduce then the efficiency of the heat exchangers.

APPROVALS

OEM's approvals: BOCK, GRASSO, HOWDEN, YORK.

CHARACTERISTICS

CHARACTERISTICS	METHODS	UNITS	PLANETELF ACD					
			32	46	68	100FY	150FY	220FY
Density at 15 °C	ISO 3675	kg/m ³	984	975	962	960	995	1018
Kinematic viscosity at 40 °C	ISO 3104	mm ² /s	34.6	48.6	69.5	101	150	220
Kinematic viscosity at 100 °C	ISO 3104	mm ² /s	6.0	7.5	9.1	11	15.5	20.8
Flash Point (COC)	ASTM D 92	°C	250	250	250	268	264	264
Pour Point	ISO 3016	°C	-54	-45	-39	-36	-33	-30
Acid number	ASTM D 974	mgKOH/g	<0.1	<0.1	<0.1	<0.1	<0.15	<0.2
Water content	KARL FISHER	ppm	< 50	< 50	< 50	< 50	< 100	< 100

Characteristics of this chart are indicative typical values

HANDLING, HEALTH AND SAFETY

Lubricants consisting of synthetic oils with specific additives.

All lubricants, of any kind, should always be handled with great care, particularly avoiding any contact with the skin.

Prevent any risk of splashing, and keep away from combustible materials.

Store under cover and away from any risk of contamination.

A safety data sheet complying with current legislation is available on [www. quickfds.com](http://www.quickfds.com) or www.lubmarine.com.

The values shown above are typical values at the date of publication. TOTAL Lubmarine reserves the right to change these typical values without prior notice.



TOTAL LUBRIFIANTS
562 avenue du Parc de l'Ile – 92029 Nanterre Cedex
Tel.: 33.1.41.35.59.23 – Fax: 33.1.41.35.20.92
www.lubmarine.com - rm.tma-diagomarplus@total.com

LUBMARINE 76/6GB - 1006