

PLANTOGEAR 100 S, 150 S, 220 S, 320 S

Environmentally acceptable lubricating oil and EP industrial gear oil based on synthetic saturated esters

Description

PLANTOGEAR S products are environmentally acceptable industrial gear oils based on special saturated synthetic esters which guarantee high ageing resistance and excellent wear protection - very good lubricity. The products have a good solvency (good deterging dispersant properties due to the polar ester base oils).

PLANTOGEAR S products have high scuffing protection (FZG > 12). The selected antiwear/ extreme pressure additive system guarantees the wear protection of bearings due to the excellent FE8 roller bearing wear test results (excellent wear protection of roller bearings under severe conditions, high load, low velocity).

Application

PLANTOGEAR S products can be used as universal CLP industrial gear oils. PLANTOGEAR S products can be used in spur, bevel, planetary and worm gears, especially in environmentally sensitive areas. The products can also be used in drive systems in water protection areas where ground and surface water can be polluted by oil leaks. The formulation of PLANTOGEAR S series is based on fully synthetic saturated high-performance esters based on natural renewable resources. The products can be used in applications where the use of synthetic lubricants are of advantage.

Specifications

The products of the PLANTOGEAR S series fulfill and surpass the requirements according to:

- DIN 51 517-3: CLP
- ISO 6743-6 and ISO 12925-1: CKC / CKD / CKE
- AGMA 9005/E02: EP

The products are listed, recommended, approved by important gear manufacturers.

Advantages

- Good corrosion protection
- Excellent wear protection for gears and bearings
- Excellent viscosity temperature behaviour, high viscosity index (VI)
- Miscible with mineral oil and polyalphaolefin gear oils
- Natural dissolving properties
- Highest shear stability
- Based on renewable resources
- Rapidly biodegradable (> 60% acc. to OECD 301 C)
- High resistance to ageing
- Good air release
- Good foaming properties
- Optimally suited for high and low temperature use



EU Ecolabel: PLANTOGEAR 100 S: DE/027/100
PLANTOGEAR 150 S: DE/027/101
PLANTOGEAR 220 S: DE/027/102
PLANTOGEAR 320 S: DE/027/103



Better for the environment...

- geringfügige Schädigung von Wasser und Boden bei der Anwendung
- enthält einen großen Anteil von Ausgangsstoffen auf biologischer Basis
- reduced harm for water and soil during use
- contains a large fraction of biobased material

better for you.

PLANTOGEAR 100 S, 150 S, 220 S, 320 S

Environmentally acceptable lubricating oil and EP industrial gear oil based on synthetic saturated esters

Instructions for use

The PLANTOGEAR S products can be used as a universal industrial gear oil in new gears as well as in used gears. New gears should be flushed and rinsed before applying PLANTOGEAR S. New gears are usually partly filled with mineral oil based corrosion protection and running in oils after manufacture. If they are not completely flushed, the running in and the corrosion protection oil remains in the gear and may contaminate the PLANTOGEAR S products. Under unfavourable conditions this can result in increased foam values and this can affect the biodegradability of the PLANTOGEAR S products negatively. The content of the residual mineral oil should, therefore, be reduced as recommended in the ISO 15380 guideline, table A1 (guidelines for changing fluid from mineral based oils to environmentally acceptable fluids) to a percentage of approximately lower than 2 % mineral oil in PLANTOGEAR S.

Old gears should also be flushed and rinsed before changing over to PLANTOGEAR S in order to reduce substantially the concentration of the residual mineral oil based product.

The internal tank and gear coatings should be compatible with ester based products.

Paints which are not compatible to esters are not recommended to be used. In general two components coating systems can be used with ester based products. The use of stainless steel tanks or stainless steel filter housings is recommended.

When deep filtration filters are used, the good solvency, dissolving properties of the PLANTOGEAR S products can reduce the filter life.

Clean/check or replace the oil filters in the system after 1 week after changing over to PLANTOGEAR S products. To ensure a safe operation, when using PLANTOGEAR S products in gear and circulating systems, remove any water that may have penetrated the systems before start-up or after longer periods of down-time. We recommend the use of suitable dryer systems and filtration units. Use ester-resistant compatible sealing materials and plastic materials in general. We recommend the use of viton material in dynamic stressed seals.

Observe the change-over recommendations according to ISO 15380.

PLANTOGEAR 100 S, 150 S, 220 S, 320 S

Environmentally acceptable lubricating oil and EP industrial gear oil based on synthetic saturated esters

Typical technical data:

		PLANTOGEAR				
Product name		100 S	150 S	220 S	320 S	
Properties	Unit					Test method
Type of lubricant acc. to DIN 51 517-3, Labeling acc. to DIN 51 502		CLP 100	CLP 150	CLP 220	CLP 320	DIN 51 502
Labeling acc. to ISO 12 925-1		CKC 100	CKC 150	CKC 220	CKC 320	ISO 12 925-1
Viscosity class acc. to DIN ISO 3448		ISO VG 100	ISO VG 150	ISO VG 220	ISO VG 320	DIN ISO 3448
Kinematic viscosity at 40 °C	mm ² /s	100	150	220	320	DIN EN ISO 3104
Viscosity index		138	145	152	155	DIN ISO 2909
Density at 15 °C	kg/m ³	0.924	0.926	0.938	0.943	DIN 51 757
Flashpoint in open cup acc. to Cleveland	°C	280	280	280	280	DIN EN ISO 2592
Pourpoint	°C	- 33	- 30	- 30	- 30	DIN ISO 3016
Neutralisation number (acidic)	mg KOH/g	0.7	0.7	0.7	0.7	DIN 51 558-1
Water content (%)	%	< 0.05	< 0.05	< 0.05	< 0.05	DIN 51 777-2
Foaming immediately and after 10 min.						ISO 6247
Seq. I, at 24 °C	ml	0/0	0/0	0/0	0/0	
Seq. II, at 93 °C	ml	20/0	20/0	10/0	0/0	
Seq. III, at 24 °C	ml	0/0	0/0	0/0	0/0	

PLANTOGEAR 100 S, 150 S, 220 S, 320 S

Environmentally acceptable lubricating oil and EP industrial gear oil based on synthetic saturated esters

Typical technical data (continued):

		PLANTOGEAR				
Product name		100 S	150 S	220 S	320 S	
Properties	Unit					Test method
Demulsifying at 54 °C	min	-	-	-	-	ISO 6614
at 82 °C (ISO VG 100 and higher)	min	15	15	20	25	
Copper corrosion (3 h, 100 °C)	degree of corrosion	1	1	1	1	DIN EN ISO 2160
Steel corrosion, method A	degree of corrosion	0 - A (pass)	0 - A (pass)	0 - A (pass)	0 - A (pass)	DIN ISO 7120
Ageing 312 h / 95 °C						DIN EN ISO 4263-4
- Increase of viscosity at 100 °C	%	3.3	3	3.5	3.7	
- Increase of viscosity number	ml	0	0	0	0	
FZG mechanical gear test rig FZG A/8.3/90	failure load stage	> 12	> 12	> 12	> 12	DIN ISO 14 635-1
FE8 wear test, D7.5/80-80,						DIN 51 819-3
- roller wear	mg	< 15	< 15	< 15	< 15	
- cage wear	mg	< 100	< 100	< 100	< 100	
Effect on seal material SRE-NBR 28/SX after 7 days ± 2 h at (100 ± 1) °C						DIN ISO 1817
Change in volume	%	7.2	7.5	5.8	4.6	
Change in hardness	%	- 6.2	- 6.7	- 5.5	- 4.0	
Change in elongation	%	- 1.2	- 1.1	- 2.2	- 3.3	
Change in tensile strength	%	- 14.1	- 11.7	- 12.3	- 16.5	



PLANTOGEAR 100 S, 150 S, 220 S, 320 S

Environmentally acceptable lubricating oil and EP industrial gear oil based on synthetic saturated esters

The information contained in this product information is based on the experience and know-how of FUCHS EUROPE SCHMIERSTOFFE GMBH in the development and manufacturing of lubricants and represents the current state-of-the-art. The performance of our products can be influenced by a series of factors, especially the specific use, the method of application, the operational environment, component pre-treatment, possible external contamination, etc. For this reason, universally-valid statements about the function of our products are not possible. The information given in this product information represents general, non-binding guidelines. No warranty expressed or implied is given concerning the properties of the product or its suitability for any given application.

We therefore recommend that you consult a FUCHS EUROPE SCHMIERSTOFFE GMBH application engineer to discuss application conditions and the performance criteria of the products before the product is used. It is the responsibility of the user to test the functional suitability of the product and to use it with the corresponding care.

Our products undergo continuous improvement. We therefore retain the right to change our product program, the products, and their manufacturing processes as well as all details of our product information sheets at any time and without warning. With the publication of this product information, all previous editions cease to be valid.

Any form of reproduction requires express prior written permission from FUCHS EUROPE SCHMIERSTOFFE GMBH.

© FUCHS EUROPE SCHMIERSTOFFE GMBH. All rights reserved.