



## Quench Oils

Quench Oils are high-quality oils developed for heat treatment of ferrous metals in a wide variety of quenching operations. They are formulated to provide deep and uniform hardening with minimum distortion and cracking for a smooth surface finish.

Quench Oils are available in four grades: 15, 22, 22HS and 32HS. The 22 grade is a highly refined, straight (non-additized) paraffinic mineral oil recommended for conventional quenching of ferrous metals at bath temperatures up to 150°F (66°C). It has a slower quench speed than the other grades, and provides minimum hardening power. The other three grades are fortified with select additives to provide enhanced oxidation resistance and metal-wetting ability for use in fast quench operations where it is important to develop maximum hardness while minimizing distortion. The 15 and 22HS grades are high-speed quench oils with moderate-to-high hardening power. The 32HS grade is a higher viscosity, high-speed quench oil that provides the highest hardening power.

Quench Oils provide a high initial cooling rate to induce maximum hardness. After the critical transformation temperature is passed, the cooling rate gradually decreases to a much slower rate to minimize the possibility of stress and metal distortion, thereby ensuring a smooth surface finish. These oils are highly stable throughout the hardening temperature range to provide long service life with minimal sludge formation. They have a high viscosity index for minimum viscosity change during the entire quenching operation, and have high flash and fire points to minimize fire hazards.

### Applications

- Conventional and fast quenching of ferrous metals, such as carbon steel, gray iron and high-alloy steel

**Caution:** Quench Oils must not be mixed with competitive quench oils, unless tested for compatibility. They are **not** recommended for marquenching or martempering operations, where oil temperatures can reach 150°C to 232°C (302°F to 450°F).

### Features/Benefits

- Controlled cooling rate to minimize cracking and distortion
- Good surface finish
- Excellent oxidation resistance and thermal stability
- High flash point for fire safety

## Metal Quenching Oils

### CONTACT INFORMATION

Phillips66  
Lubricants.com

U.S. Customer  
Service:  
**1-800-368-7128**

Technical Hotline:  
**1-877-445-9198**

International  
Customer Service:  
**1-832-765-2500**

E-mail address:  
lubricants@  
p66.com



**Note:** Agitation, filtration and periodic product sweetening are essential to successful quenching operations. The quench tanks must be periodically cleaned and the quench oil filtered to remove scale, metal shavings and contaminants. A 50-micron double-bag filter is recommended for proper maintenance. The quench oil must be continuously agitated to provide uniform surface microstructure. Condition monitoring by oil analysis is essential in maintaining optimum performance and the desired quenching qualities of these oils.

### Quench Oils

#### Typical Properties

Grade	15	22	22HS	32HS
ISO Grade	15	22	22	32
Specific Gravity @ 60°F	0.861	0.854	0.855	0.864
Density, lbs/gal @ 60°F	7.17	7.11	7.12	7.19
Color, ASTM D1500	5.0	0.0	L 2.0	2.0
Flash Point (COC), °C (°F)	185 (365)	205 (401)	207 (405)	218 (424)
Pour Point, °C (°F)	-15 (5)	-13 (9)	-15 (5)	-15 (5)
Viscosity,				
cSt @ 40°C	16.1	22.0	23.1	32.9
cSt @ 100°C	3.5	4.5	4.5	5.5
SUS @ 100°F	87.3	115	120	170
SUS @ 210°F	38.1	41.4	41.4	44.7
Viscosity Index	90	118	107	103
Acid Number, ASTM D974, mg KOH/g	0.35	0.01	0.12	0.05
Cooling Characteristics <sup>(1)</sup> , ASTM D6200,				
Maximum Cooling Rate, °C/sec	94-106	47-58	92-103	94-105
Maximum Cooling Rate, °F/sec	170-190	85-105	165-185	169-189
Time to Cool to 600°C (1,112°F), seconds	8-10	12-15	9-10	9-10

<sup>(1)</sup>**Note:** Values for cooling rates and quench speeds are typical for new oil. For used oil, the values will vary due to aging and contamination.

### Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3apps.phillips66.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

© 2015 Phillips 66 Company, Phillips 66, 76, Conoco, Liquid Titanium and their respective logos and products are trademarks of Phillips 66 Company in the U.S.A. and other countries.